

## DUPLEX STAINLESS STEEL

AISI type	UNS	C	Mn	Si	Cr	Ni	Mo	Other
3RE60	S 31500	0.03	1.20-2.00	1.40-2.00	18.00-19.00	4.25-5.25	2.50-3.00	-
7-Mo plus	S 32950	0.03	2.00	0.60	26.00-29.00	3.50-5.20	1.00-2.50	0.15-0.35 N
44 LN	S 31200	0.03	2.00	1.00	24.00-26.00	5.50-6.50	1.20-2.00	0.14-0.20 N
2205	S 31803	0.03	2.00	1.00	21.00-23.00	4.50-6.50	2.50-3.50	0.08-0.20 N
2304	S 32304	0.03	2.50	1.00	21.50-24.50	3.00-5.50	-	0.05-0.06 Cu, 0.05-0.20 N
2507	S 32750	0.03	1.20	0.80	24.00-26.00	6.00-8.00	3.00-5.00	0.24-0.32 N
AF 918	S 39277	0.02	-	0.80	24.00-26.00	6.50-8.00	3.00-4.00	1.20-2.00 CU, 0.23-0.33 N, 0.80-1.20 W
DP 3	S 31260	0.03	1.00	0.75	24.00-26.00	5.50-7.50	2.50-3.50	0.20-0.80 CU, 0.10-0.30 N, 0.10-0.50 W
DP3W	S 39274	0.03	1.00	0.80	24.00-26.00	6.00-8.00	2.50-3.50	0.20-0.80 Cu, 0.24-0.32 N, 1.50-2.50 W
Ferrallium 255	S 32550	0.04	1.50	1.00	24.00-27.00	4.50-6.50	2.90-3.90	1.50-2.50 Cu, 0.10-0.25 N
Uranus 50	S 32404	0.04	2.00	1.00	20.50-22.50	5.50-8.50	2.00-3.00	1.00-2.00 Cu, 0.20 N
Zeron 100	S 32760	0.03	1.00	1.00	24.00-26.00	6.00-8.00	3.00-4.00	0.50-1.00 Cu, 0.20-0.30 N, 0.50-1.00 W

AmEuro Metals developed this information from several sources and technical literature. AmEuro Metals assumes no responsibility for the accuracy of this information.