

## FRENCH SPECIFICATIONS FOR AIRCRAFT ALLOYED STEEL BARS & COMPARISON AMS/WERKSTOFFNUMMER.

Air 9160 specs	AMS	W-nr	C	Mn	Cr	Mo	Ni	V	Nb	Other elements
15CDV6		1.7734	0.15	1.00	1.35	0.90		0.25		
16NCD13		1.6657	0.17	0.45	1.00	0.25	3.25			
16NCD 17		1.6722	0.16	0.40	1.20	0.22	4.10			
30NCD16		1.6747	0.30	0.50	1.40	0.45	4.00			
35NCD16			0.37	0.45	1.80	0.45	4.00			
25CD4S		1.7214	0.25	0.70	1.00	0.20				
30CD12		1.8564	0.30	0.50	3.00	0.40				
35CD4		1.7220	0.34	0.70	1.00	0.20				
40CDV12		1.8523	0.40	0.55	3.25	1.00		0.20		
100C6	6440	1.3505	1.00	0.30	1.50					
Z12CNDV12	5719	1.4939	0.11		11.50	1.60	2.60	0.30		0.03% N
Z15CN17.03		1.4044	0.16		16.50		2.40			
EZ2NKD18	6512	1.6359	0.01	0.05		5.00	18.00			8.0% Co+Al/Ti